

EPS® 2763

All-Acrylic Emulsion

MARKET SEGMENT: CONSTRUCTION

COMMON APPLICATIONS: TOPCOAT, ADMIX

EPS® 2763 is a self-crosslinking, soft acrylic emulsion with excellent flexibility, elongation and dirt pickup resistance (DPUR). This polymer is designed for use in a variety of high-performance applications like roof coatings, coatings for masonry substrates and in cement admix. It provides especially good adhesion to cement and rubber particles such as those used in running tracks, playground surfaces and tennis courts. Coatings formulated with EPS® 2763 exhibit excellent water resistance, crack resistance and adhesion.

PERFORMANCE BENEFITS

- Water resistance
- Flexibility and elongation
- Adhesion
- Exterior durability
- Dirt pickup resistance (DPUR)
- Crack resistance on cement substrates
- Compatible with cement substrates

TYPICAL PROPERTIES

Weight Solids	58.0%
Weight/Gallon	8.80
pH	8.0
Volume Solids	55.6%
MFFT	0° C

Questions? Call EPS Customer Service @ 1-800-654-4242 / Email: info@eps-materials.com

8/3/2023

SDS: For details on health, safety and handling information, Safety Data Sheets (SDS) are available at www.epscca.com.

The data on this sheet represent typical values. Since application variables are a major factor in product performance, this information should serve only as a general guide. EPS assumes no obligation or liability for use of this information. UNLESS EPS AGREES OTHERWISE IN WRITING, EPS MAKES NO WARRANTIES, EXPRESS OR IMPLIED, AND DISCLAIMS ALL IMPLIED WARRANTIES INCLUDING WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE OR FREEDOM FROM PATENT INFRINGEMENT. EPS WILL NOT BE LIABLE FOR ANY SPECIAL, INCIDENTAL OR CONSEQUENTIAL DAMAGES. Your only remedy for any defect in this product is the replacement of the defective product, or a refund of its purchase price, at our option. Unless otherwise agreed in writing, all sales of EPS products are governed by the EPS Terms and Conditions of Sale, available at <https://www.epscca.com/galleries/pdfs/salesterms.pdf>.