

## Cementitious Substrates

### CONCRETE CURE & SEAL – WATER BASED

Product	NVM	MFFT °C	Tg °C	Properties	Applications
EPS 2272	50.0	42	10	<ul style="list-style-type: none"> <li>▪ Excellent moisture retention</li> <li>▪ Excellent blush resistance</li> <li>▪ Good acid and alkali resistance</li> <li>▪ Able to formulate &lt; 100 g/l VOC</li> </ul>	<ul style="list-style-type: none"> <li>▪ ASTM C-1315 Type I Class C cure &amp; seal</li> </ul>

### CONCRETE CURE & SEAL – SOLVENT BASED

Product	NVM	Solvent	Visc.	Reduced Visc. @ 25% in A100	Properties	Applications
EPS 7725	50	A100	Z-Z2.5	A - B	<ul style="list-style-type: none"> <li>▪ Excellent 'holdout'</li> <li>▪ Excellent gloss development</li> </ul>	<ul style="list-style-type: none"> <li>▪ ASTM C-1315 Type I Class C cure &amp; seal</li> <li>▪ Wet look sealers</li> </ul>

rev. 05/26/11

**Questions? Call EPS Technical Service @ 1-800-601-8111**

The data on this sheet represent typical values. Since application variables are a major factor in product performance, this information should serve only as a general guide. EPS assumes no obligation or liability for use of this information. UNLESS EPS AGREES OTHERWISE IN WRITING, EPS MAKES NO WARRANTIES, EXPRESS OR IMPLIED, AND DISCLAIMS ALL IMPLIED WARRANTIES INCLUDING WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR USE OR FREEDOM FROM PATENT INFRINGEMENT. EPS WILL NOT BE LIABLE FOR ANY SPECIAL, INCIDENTAL OR CONSEQUENTIAL DAMAGES. Your only remedy for any defect in this product is the replacement of the defective product, or a refund of its purchase price, at our option.