

HIGH-PERFORMANCE RESINS FOR CONSTRUCTION COATINGS

EPS[®] 2526 Concrete Sealer, Topcoat	EPS[®] 2252 TPO Primer			
EPS[®] 2257 Concrete Sealer	EPS[®] 2224 Roof Coatings			
EPS[®] 2293 Non-Blushing Concrete Sealer				
EPS[®] 2272 Concrete Cure & Seal	EPS[®] 2533 Universal Primer			
EPS[®] 7725 Concrete Cure & Seal Solution Acrylic	EPS[®] 2719 Roof Coatings			
	EPS[®] 2559 Waterproofer, Tile Mastics			
EPS[®] 7501 Concrete Cure & Seal Solution Acrylic	EPS[®] 2708 All-Acrylic Multi-Faceted Polymer			EPS[®] 2224 ASTM C834 Caulk
Cure & Seal	Construction Coatings	Mastics	Concrete Admix	Sealants



Product	Application / Chemistry	Solids (%)	pH Value	MFFT (°C)	Tg (°C)	Weight per Gal (lb)
EPS® 2252	Roof Coatings, TPO primer All-Acrylic	60	8.0 - 9.0	-	-32	8.55
EPS® 2719	Roof Coatings All-Acrylic	55	8.0 - 8.5	-	-4	8.85
EPS® 2224	Roof Coatings; ASTM C 834 Caulk All-Acrylic	58	3.5 - 5.0	-	-11	8.70
EPS® 2272	Cure & Seal Styrenated Acrylic	50	7.8 - 8.0	42	-	8.55
EPS® 2257	Concrete Sealer All-Acrylic	40	8.0 - 9.0	7	-	8.80
EPS® 2293	Concrete Sealer All-Acrylic	40	8.0 - 9.0	< 10	-	8.70
EPS® 2526	Concrete Sealer, Topcoat Styrenated Acrylic	40	7.5 - 8.5	> 60	-	8.70
EPS® 2533	Universal Primer Styrenated Acrylic	45.5	7.0 - 8.0	9	-	8.60
EPS® 2559	Coatings / Mastics Styrenated Acrylic	50	7.0 - 8.0	44	-	8.70
EPS® 2708	Coatings / Mastics Polymer Admix All-Acrylic	50	8.0 - 9.0	20	-	8.80

Product	Application Chemistry	Solids (%)	Solvent	Viscosity	Weight per Gal (lb)
EPS® 7501	Cure & Seal Solution Acrylic	55	Aromatic 100	W - Z	8.05
EPS® 7725	Cure & Seal Solution Acrylic	50	Aromatic 100	Z - Z 2½	7.95

THE EXPERTISE BEHIND THE INNOVATION

The data on this sheet represents typical values. Since application variables are a major factor in product performance, this information should serve only as a general guide. EPS assumes no obligation or liability for use of this information. UNLESS EPS AGREES OTHERWISE IN WRITING, EPS MAKES NO WARRANTIES, EXPRESS OR IMPLIED, AND DISCLAIMS ALL IMPLIED WARRANTIES INCLUDING WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR

PURPOSE OR FREEDOM FROM PATENT INFRINGEMENT. EPS WILL NOT BE LIABLE FOR ANY SPECIAL, INCIDENTAL OR CONSEQUENTIAL DAMAGES. Your only remedy for any defect in this product is the replacement of the defective product, or a refund of its purchase price, at our option. Unless otherwise agreed in writing, all sales of EPS products are governed by the EPS Terms and Conditions of Sale, available at <https://www.epscca.com/galleries/pdfs/salesterms.pdf>.

CONTACT INFORMATION

EPS Headquarters
1400 N. State St.
Marengo, Illinois 60152

Sales and Customer Service
Phone: 1-800-654-4242
Email: info@epscca.com

EPS Technical Service
Phone: 1-800-654-4242
Email: info@eps-materials.com

epscca.com