



## ARCHITECTURAL

Product	Chemistry	Coating Type	Substrate	Applications					Properties				Performance Attributes
				Trim Paints	Lazure	Masonry	Deck Stain	Floor (Mineral, Wood)	Solids (%)	Viscosity, 23°C [mPa·s]	pH (-)	MFFT (°C)	
EPS® 294	Self-crosslinking multiphase acrylic emulsion	Topcoat	Concrete, Exterior Wall, Interior Wall, Masonry/Stucco			●	●		40	< 500	8.0-9.0	12	<ul style="list-style-type: none"> <li>Adhesion</li> <li>Abrasion resistance</li> <li>Chemical resistance</li> </ul>
EPS® 572	Self-crosslinking acrylic copolymer	Topcoat	Exterior Wall, Interior Wall, Masonry/Stucco, Wood	●					45	200-800	8.0-9.0	17	<ul style="list-style-type: none"> <li>High gloss</li> <li>Block/alkali resistance</li> <li>Wet adhesion</li> <li>Water resistance</li> </ul>
EPS® 706	All-acrylic emulsion	Basecoat, Topcoat	Exterior Wall, Interior Wall, Wood		●	●			55	< 500	8.5-9.0	10	<ul style="list-style-type: none"> <li>Exterior durability</li> <li>Dirt pickup resistance (DPUR)</li> <li>Hydrophobic</li> </ul>
EPS® 747	Self-crosslinking acrylic copolymer	Topcoat	Exterior Wall, Interior Wall, Masonry/Stucco, Wood	●	●				44.5	< 500	7.0-8.0	5	<ul style="list-style-type: none"> <li>Exterior durability</li> <li>Block resistance</li> <li>Water resistance</li> <li>Flat through gloss coatings</li> </ul>

All these polymers are formulated without the use of intentionally added fluorosurfactants.

## THE EXPERTISE BEHIND THE INNOVATION

The data on this sheet represents typical values. Since application variables are a major factor in product performance, this information should serve only as a general guide. EPS assumes no obligation or liability for use of this information. UNLESS EPS AGREES OTHERWISE IN WRITING, EPS MAKES NO WARRANTIES, EXPRESS OR IMPLIED, AND DISCLAIMS ALL IMPLIED WARRANTIES INCLUDING WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE OR FREEDOM FROM PATENT INFRINGEMENT. EPS WILL NOT BE LIABLE FOR ANY SPECIAL, INCIDENTAL OR CONSEQUENTIAL DAMAGES. Your only remedy for any defect in this product is the replacement of the defective product, or a refund of its purchase price, at our option. Unless otherwise agreed in writing, all sales of EPS products are governed by the EPS Terms and Conditions of Sale, available at <https://www.epcca.com/galleries/pdfs/salesterms.pdf>.

### CONTACT INFORMATION

Nijverheidsweg 35  
3341 LJ H.I. Ambacht  
The Netherlands

Phone: +31 78 683 3250  
Email: [info.nl@eps-materials.com](mailto:info.nl@eps-materials.com)  
[epcca.com/en\\_GB/](https://www.epcca.com/en_GB/)