



CONSTRUCTION

Product	Chemistry	Coating Type	Substrate	Applications				Properties				Performance Attributes	
				Roof Coatings	Line Marking	Roofing/Siding	Sealers	GFR	Solids (%)	Viscosity, 23°C [mPa·s]	pH (-)		MFFT (°C)
EPS® 293	Self-crosslinking all-acrylic emulsion	Sealer, Topcoat	Asphalt, Concrete			●			40	< 500	8.0-9.0	12	<ul style="list-style-type: none"> Adhesion Abrasion resistance Chemical resistance
EPS® 506	Acrylic copolymer	Primer, Topcoat	Concrete, Masonry/Stucco			●			50	< 500	8.0-9.0	26	<ul style="list-style-type: none"> Multi-substrate adhesion Hydrophobic Exterior durability
EPS® 717	High-solids all-acrylic copolymer	Topcoat	Concrete, Exterior Wall, Masonry/Stucco	●					55	< 500	9.5-10.2	17	<ul style="list-style-type: none"> Fast dry Abrasion resistance Low odour
EPS® 719	All-acrylic emulsion	Basecoat, Topcoat	Asphalt, Metal	●					55	< 1000	8.0-8.5	10	<ul style="list-style-type: none"> Asphalt bleed blocker Dirt pickup resistance (DPUR) Exterior durability
EPS® 730	Acrylic copolymer	Primer, Sealer	Concrete, Exterior Wall, Interior Wall, Masonry/Stucco			●			30	< 500	8.0-9.0	0	<ul style="list-style-type: none"> Ultrafine particle size Stabilisation of powdery cementitious substrates
FORTON™ VF 774 AF	Acrylic copolymer	Modifier for glass fibre reinforced concrete	Concrete				●		51	50-300	8.0-10.0	11	<ul style="list-style-type: none"> Glass fibre reinforced cement Concrete repair

THE EXPERTISE BEHIND THE INNOVATION

The data on this sheet represents typical values. Since application variables are a major factor in product performance, this information should serve only as a general guide. EPS assumes no obligation or liability for use of this information. UNLESS EPS AGREES OTHERWISE IN WRITING, EPS MAKES NO WARRANTIES, EXPRESS OR IMPLIED, AND DISCLAIMS ALL IMPLIED WARRANTIES INCLUDING WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE OR FREEDOM FROM PATENT INFRINGEMENT. EPS WILL NOT BE LIABLE FOR ANY SPECIAL, INCIDENTAL OR CONSEQUENTIAL DAMAGES. Your only remedy for any defect in this product is the replacement of the defective product, or a refund of its purchase price, at our option. Unless otherwise agreed in writing, all sales of EPS products are governed by the EPS Terms and Conditions of Sale, available at <https://www.epscca.com/galleries/pdfs/salesterms.pdf>.

CONTACT INFORMATION

Nijverheidsweg 35
3341 LJ H.I. Ambacht
The Netherlands

Phone: +31 78 683 3250
Email: info.nl@eps-materials.com
epscca.com/en_GB/