



INDUSTRIAL METAL

Product	Chemistry	Coating Type	Substrate	Applications					Properties				Performance Attributes
				ACE	Maintenance	General Industry	Tube & Piping	Specialty	Solids (%)	Viscosity 23°C [mPa·s]	pH (-)	MFFT (°C)	
EPS® 541	Acrylic copolymer	Topcoat	Metal		●	●			50	< 500	7.5-8.5	57	<ul style="list-style-type: none"> Adhesion Chemical and corrosion resistance with anti-corrosive pigments Exterior durability
EPS® 546	Acrylic copolymer	Topcoat	Glass, Metal, Wood				●		30	< 500	9.0-10.0	1	<ul style="list-style-type: none"> Alkali strippable Temporary protection of metal Shade protection for greenhouses Open time expander
EPS® 563	Acrylic copolymer	Topcoat	Glass, Metal	●	●	●			45.5	< 500	8.5-9.5	N/A	<ul style="list-style-type: none"> No popping at high film thickness High gloss Chemical resistance OH functional, use in combination with isocyanate or melamine
EPS® 595	Acrylic copolymer	Basecoat, Topcoat	Metal	●	●	●			50	< 500	8.0-9.0	22	<ul style="list-style-type: none"> Multi-substrate adhesion Corrosion resistance (up to C5) Hydrophobic High gloss
DYFLEX® LP 9624	Acrylic copolymer	Basecoat, Topcoat	Metal, Wood		●	●			42	< 250	7.4-8.4	46	<ul style="list-style-type: none"> High gloss Chemical and corrosion resistance Exterior durability

THE EXPERTISE BEHIND THE INNOVATION

The data on this sheet represents typical values. Since application variables are a major factor in product performance, this information should serve only as a general guide. EPS assumes no obligation or liability for use of this information. UNLESS EPS AGREES OTHERWISE IN WRITING, EPS MAKES NO WARRANTIES, EXPRESS OR IMPLIED, AND DISCLAIMS ALL IMPLIED WARRANTIES INCLUDING WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE OR FREEDOM FROM PATENT INFRINGEMENT. EPS WILL NOT BE LIABLE FOR ANY SPECIAL, INCIDENTAL OR CONSEQUENTIAL DAMAGES. Your only remedy for any defect in this product is the replacement of the defective product, or a refund of its purchase price, at our option. Unless otherwise agreed in writing, all sales of EPS products are governed by the EPS Terms and Conditions of Sale, available at <https://www.epasca.com/galleries/pdfs/salesterms.pdf>.

CONTACT INFORMATION

Nijverheidsweg 35
3341 LJ H.I. Ambacht
The Netherlands

Phone: +31 78 683 3250
Email: info.nl@eps-materials.com
[epasca.com/en_GB/](https://www.epasca.com/en_GB/)