

## HIGH-PERFORMANCE ARCHITECTURAL COATINGS

Topcoat	<b>EPS® 2706</b> Interior/Exterior; Exterior durability; efflorescence and dirt pickup resistance				
	<b>EPS® 2741</b> Interior/Exterior; Scrub resistance, stain removal and washability				
	<b>EPS® 2786</b> Interior/Exterior; Near zero VOC without fluorosurfactants, hot block resistance				
Primers	<b>EPS® 2533</b> Interior/Exterior; Stain blocking, water resistance				
	<b>RayVace® 331</b> Interior; Good stability and high pigment loading				
Specialty	<b>EPS® 9147</b> Low VOC Coalescent				
	Flat	Eggshell	Satin	Semi-Gloss	High Gloss

Product	Chemistry	Solids (%)	pH	MFFT (°C)
EPS® 2533	Styrenated Acrylic	45.5	7.0-8.0	9
EPS® 2706	All-Acrylic	55.0	8.0-8.5	4
EPS® 2741	All-Acrylic	50.0	8.5-9.0	10
EPS® 2786	All-Acrylic	48.0	8.5-9.0	21
RayVace® 331	Vinyl Acrylic	60.0	4.0-5.0	10
EPS® 9147	Coalescent	>99.1	-	-

### THE EXPERTISE BEHIND THE INNOVATION

The data on this sheet represents typical values. Since application variables are a major factor in product performance, this information should serve only as a general guide. EPS assumes no obligation or liability for use of this information. UNLESS EPS AGREES OTHERWISE IN WRITING, EPS MAKES NO WARRANTIES, EXPRESS OR IMPLIED, AND DISCLAIMS ALL IMPLIED WARRANTIES INCLUDING WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR

PURPOSE OR FREEDOM FROM PATENT INFRINGEMENT. EPS WILL NOT BE LIABLE FOR ANY SPECIAL, INCIDENTAL OR CONSEQUENTIAL DAMAGES. Your only remedy for any defect in this product is the replacement of the defective product, or a refund of its purchase price, at our option. Unless otherwise agreed in writing, all sales of EPS products are governed by the EPS Terms and Conditions of Sale, available at [www.epscca.com/galleries/pdfs/salesterms.pdf](http://www.epscca.com/galleries/pdfs/salesterms.pdf).

### CONTACT INFORMATION

EPS Headquarters  
1400 N. State St.  
Marengo, Illinois 60152

Sales and Customer Service  
Phone: 800-654-4242  
Email: [info@epscca.com](mailto:info@epscca.com)

EPS Technical Service  
Phone: 800-654-4242  
Email: [info@eps-materials.com](mailto:info@eps-materials.com)

[epscca.com](http://epscca.com)