



## HIGH-PERFORMANCE ARCHITECTURAL PRODUCTS

Product	Chemistry	Coating Type	Substrate	Finish					Properties			Performance Benefits
				Flat	Eggshell	Satin	Semigloss	High Gloss	Solids (%)	pH	MFFT (°C)	
<b>EPS® 2533</b>	Styrenated Acrylic	Primer	Concrete, Exterior Wall, Interior Wall, Masonry/ Stucco, Metal, Wood	•					45.5	7.0-8.8	9	<ul style="list-style-type: none"> <li>Interior/exterior</li> <li>Stain blocking</li> <li>Water resistance</li> </ul>
<b>EPS® 2706</b>	All-Acrylic	Topcoat	Concrete, Exterior Wall, Interior Wall, Wood	•	•	•	•		55	8.0-8.5	4	<ul style="list-style-type: none"> <li>Interior/exterior</li> <li>High alkali stability</li> <li>Abrasion resistance and adhesion</li> </ul>
<b>EPS® 2731</b>	All-Acrylic	Topcoat	Concrete, Exterior Wall, Interior Wall, Wood	•	•	•	•		50	8.5-9.0	15	<ul style="list-style-type: none"> <li>Interior/exterior</li> <li>Dirt pickup resistance</li> <li>Color fade and efflorescence resistance on alkali substrates</li> <li>Surfactant leaching resistance</li> </ul>
<b>EPS® 2736</b>	All-Acrylic	Topcoat	Concrete, Exterior Wall, Interior Wall, Wood	•	•	•			58.5	8.0-9.0	10-12	<ul style="list-style-type: none"> <li>Interior/exterior</li> <li>Dirt pickup resistance</li> <li>Color retention and UV resistance</li> <li>Performs well over alkaline substrates</li> </ul>
<b>EPS® 2746</b>	All-Acrylic	Topcoat	Concrete, Exterior Wall, Interior Wall, Wood	•	•	•	•		50	8.5-9.0	10	<ul style="list-style-type: none"> <li>Interior/exterior</li> <li>Near-zero VOC capable</li> <li>Scrub resistance</li> <li>Stain removal and washability</li> </ul>
<b>EPS® 2786</b>	All-Acrylic	Topcoat	Concrete, Exterior Wall, Interior Wall, Masonry/ Stucco, Wood				•	•	48	8.5-9.0	21	<ul style="list-style-type: none"> <li>Interior/exterior</li> <li>Near-zero VOC capable</li> <li>Hardness</li> <li>Dirt pickup and hot block resistance</li> </ul>
<b>RayVace® 331</b>	Vinyl Acrylic	Primer	Exterior Wall, Interior Wall, Masonry/Stucco	•					60	4.0-5.0	10	<ul style="list-style-type: none"> <li>Interior</li> <li>Good stability</li> <li>High pigment loading</li> </ul>
<b>EPS® 9147</b>	Coalescent	Specialty	-	•	•	•	•	•	>99.1	-	-	<ul style="list-style-type: none"> <li>Low VOC coalescent</li> </ul>

All of these polymers are formulated without the use of intentionally added fluorosurfactants.

## THE EXPERTISE BEHIND THE INNOVATION

The data on this sheet represents typical values. Since application variables are a major factor in product performance, this information should serve only as a general guide. EPS assumes no obligation or liability for use of this information. UNLESS EPS AGREES OTHERWISE IN WRITING, EPS MAKES NO WARRANTIES, EXPRESS OR IMPLIED, AND DISCLAIMS ALL IMPLIED WARRANTIES INCLUDING WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE OR FREEDOM FROM PATENT INFRINGEMENT. EPS WILL NOT BE LIABLE FOR ANY SPECIAL, INCIDENTAL OR CONSEQUENTIAL DAMAGES. Your only remedy for any defect in this product is the replacement of the defective product, or a refund of its purchase price, at our option. Unless otherwise agreed in writing, all sales of EPS products are governed by the EPS Terms and Conditions of Sale, available at <https://www.epscsa.com/galleries/pdfs/salesterms.pdf>.

## CONTACT INFORMATION

**EPS Headquarters**  
1400 N. State St.  
Marengo, Illinois 60152

**Sales and Customer Service**  
Phone: 800-654-4242  
Email: [info@epscsa.com](mailto:info@epscsa.com)

**EPS Technical Service**  
Phone: 800-654-4242  
Email: [info@eps-materials.com](mailto:info@eps-materials.com)