



HIGH-PERFORMANCE SPECIALTY PRODUCTS

		RayCryl® 1837 Hard and stiff all-acrylic emulsion	
EPS® 2574 Rapid block resistance, hardness	RayRez® 66 General ink formulations	RayCryl® 1856 Soft and flexible film	
EPS® 2775 ACMI-capable artist paints	RayRez® 169 Flexographic, gravure, and roll coater ink formulations	RayCryl® 1859 Medium flexible film	EPS® 9147 Near-zero VOC capable coalescent
Arts & Crafts	Graphic Arts	Nonwovens & Textiles	Specialty Products

Product	Chemistry	Solids (%)	pH	Tg (°C)
EPS® 2574	Styrenated Acrylic	50.0	8.0-9.0	53 (MFFT)
EPS® 2775	All-Acrylic	50.0	8.5-9.0	13 (MFFT)
RayCryl® 1837	All-Acrylic	50.0	3.5-4.5	41
RayCryl® 1856	All-Acrylic	55.0	3.5-4.5	36
RayCryl® 1859	All-Acrylic	55.0	3.5-4.5	7
RayRez® 66	Styrenated Acrylic	46.0	9.0-9.5	40
RayRez® 169	Styrenated Acrylic	46.0	8.5-9.5	-25
EPS® 9147	Coalescent	>99.1	-	-

THE EXPERTISE BEHIND THE INNOVATION

The data on this sheet represents typical values. Since application variables are a major factor in product performance, this information should serve only as a general guide. EPS assumes no obligation or liability for use of this information. UNLESS EPS AGREES OTHERWISE IN WRITING, EPS MAKES NO WARRANTIES, EXPRESS OR IMPLIED, AND DISCLAIMS ALL IMPLIED WARRANTIES INCLUDING WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR

PURPOSE OR FREEDOM FROM PATENT INFRINGEMENT. EPS WILL NOT BE LIABLE FOR ANY SPECIAL, INCIDENTAL OR CONSEQUENTIAL DAMAGES. Your only remedy for any defect in this product is the replacement of the defective product, or a refund of its purchase price, at our option. Unless otherwise agreed in writing, all sales of EPS products are governed by the EPS Terms and Conditions of Sale, available at www.epscca.com/galleries/pdfs/salesterms.pdf.

CONTACT INFORMATION

EPS Headquarters
1400 N. State St.
Marengo, Illinois 60152

Sales and Customer Service
Phone: 800-654-4242
Email: info@epscca.com

EPS Technical Service
Phone: 800-654-4242
Email: info@eps-materials.com

epscca.com