



CONSTRUCTION

Product	Chemistry	Coating Type	Substrate	Admixtures			Concrete	Elastomeric and Roof Coatings	Solids (%)	pH	MFFT (°C)	Performance Benefits
				Sheen								
EPS® 2103	All-Acrylic	Basecoat, topcoat	-	●					46.5	8.5-9.5	7	<ul style="list-style-type: none">• Dirt pickup resistance• Alkali stability• Flexibility• Low odor
EPS® 2210	All-Acrylic	Topcoat	Asphalt, Concrete				●		55	7.5-8.5	-12 (Tg)	<ul style="list-style-type: none">• ASTM D6083 Type II capable• Dirt pickup resistance• Asphalt bleed-through resistance• Excellent balance of tensile and elongation properties
EPS® 2224	All-Acrylic	Topcoat	Concrete, Masonry/ Stucco, Metal, Wood				●		58	3.5-5.5	-11 (Tg)	<ul style="list-style-type: none">• Dirt pickup resistance• Alkali and water resistance• Adhesion• Flexibility
EPS® 2252	All-Acrylic	Basecoat, primer	Asphalt, EPDM, Metal, TPO				●		60	8.0-9.0	-32 (Tg)	<ul style="list-style-type: none">• Adhesion to TPO and EPDM• <50 g/L VOC capable
EPS® 2257	All-Acrylic	Sealer	Concrete, Masonry/ Stucco		●				40	8.0-9.0	7	<ul style="list-style-type: none">• Penetration• Early water resistance• Blush and yellowing resistance
EPS® 2272	Styrenated Acrylic	Sealer	Concrete				●		50	7.0-8.0	42	<ul style="list-style-type: none">• Water retention properties• Blush resistance• Water resistance
EPS® 2293	All-Acrylic	Sealer, topcoat	Concrete, Masonry/ Stucco, Wood		●				40	8.0-9.0	<10	<ul style="list-style-type: none">• Blush and chemical resistance• Early water resistance• Exterior durability• Gloss development and retention
EPS® 2526	Styrenated Acrylic	Sealer, topcoat	Concrete, Masonry/ Stucco		●				40	7.5-8.5	>60	<ul style="list-style-type: none">• Hardness• Hot tire pickup resistance• Gloss and film clarity• Blush resistance
EPS® 2533	Styrenated Acrylic	Primer, topcoat	Concrete, Exterior Wall, Interior Wall, Masonry/ Stucco, Metal, Wood		●				45.5	7.0-8.0	9	<ul style="list-style-type: none">• Efflorescence resistance• Alkali resistance, ideal for use on “hot” cementitious substrates• Early water resistance• Exterior durability



CONSTRUCTION

				Admixtures		Concrete		Elastomeric and Roof Coatings		Solids (%)		pH		MFFT (°C)	
Product	Chemistry	Coating Type	Substrate	Sheen			Properties					Performance Benefits			
EPS® 2559	Styrenated Acrylic	Primer, topcoat	Masonry/Stucco, Metal, Wood		●			50	7.0-8.0	44	● ASTM D7088-04 capable - resistance to hydrostatic pressure ● Early water and humidity resistance ● Adhesion to concrete and masonry substrates				
EPS® 2708	All-Acrylic	Topcoat	Concrete, Exterior Wall, Interior Wall, Wood	●	●			50	8.0-9.0	20	● High alkali stability ● Abrasion resistance ● Adhesion, durability and flexibility ● Good balance of flexibility and hardness				
EPS® 2719	All-Acrylic	Basecoat, topcoat	Asphalt, Metal			●		55	8.0-8.5	4 (Tg)	● Asphalt bleed-through resistance ● Dirt pickup resistance ● Adhesion ● Excellent toughness with both high tensile strength and elongation				
RayCryl® 1008	All-Acrylic	Primer, topcoat, sealer	Concrete		●			45	8.5-9.5	16	● Dirt pickup and water resistance ● Hot tire pickup resistance ● Resistant to garage and household chemicals ● Blush resistance				
RayFlex® 765	Styrenated Acrylic	Topcoat	Asphalt, Concrete			●		50	7.2-7.7	-26 (Tg)	● Elongation and tensile strength ● Water resistance ● Low temperature flexibility ● Shear stability and high pigment loading				

THE EXPERTISE BEHIND THE INNOVATION

The data on this sheet represents typical values. Since application variables are a major factor in product performance, this information should serve only as a general guide. EPS assumes no obligation or liability for use of this information. UNLESS EPS AGREES OTHERWISE IN WRITING, EPS MAKES NO WARRANTIES, EXPRESS OR IMPLIED, AND DISCLAIMS ALL IMPLIED WARRANTIES INCLUDING WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE OR FREEDOM FROM PATENT INFRINGEMENT. EPS WILL NOT BE LIABLE FOR ANY SPECIAL, INCIDENTAL OR CONSEQUENTIAL DAMAGES. Your only remedy for any defect in this product is the replacement of the defective product, or a refund of its purchase price, at our option. Unless otherwise agreed in writing, all sales of EPS products are governed by the EPS Terms and Conditions of Sale, available at <https://www.epscsa.com/galleries/pdfs/salesterms.pdf>.

CONTACT INFORMATION

EPS Headquarters
1400 N. State St.
Marengo, Illinois 60152

Sales and Customer Service
Phone: 800-654-4242
Email: info@epscsa.com

EPS Technical Service
Phone: 800-654-4242
Email: info@eps-materials.com

[epscsa.com](https://www.epscsa.com)