

# EPS<sup>®</sup> 2156 ACRYLIC EMULSION

## DATA SHEET

### Description

EPS 2156 is an all acrylic emulsion with pressure sensitive adhesive properties for use in various applications. Typical values below are for the neat polymer.

- ✓ 180° Peel (PSTC-101) – 11 ounces/inch
- ✓ Polyken Probe Tack (ASTM D2979) – 230grams/cm<sup>2</sup>
- ✓ Static Shear (PSTC-107) - >10,000 minutes (1"x1"x1Kg)

### Tentative or Typical Properties

*Weight Solids\**: 55.5 ± 1.0%

*Weight/Gallon\**: 8.59 ± 0.10

*Tg (measured)*: -41°C

*pH*: 7.0 to 9.0

*Viscosity (#2 @20 rpm)*: N/A

*Acid Value (on solids)*: N/A

*Flash Point*: >212 °F

### Suggested Formulations

none

\*Product specification

rev 1 Feb 2019

**Questions? Call EPS Technical Service @ 1-800-601-8111**

The data on this sheet represent typical values. Since application variables are a major factor in product performance, this information should serve only as a general guide. EPS assumes no obligation or liability for use of this information. **UNLESS EPS AGREES OTHERWISE IN WRITING, EPS MAKES NO WARRANTIES, EXPRESS OR IMPLIED, AND DISCLAIMS ALL IMPLIED WARRANTIES INCLUDING WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR USE OR FREEDOM FROM PATENT INFRINGEMENT. EPS WILL NOT BE LIABLE FOR ANY SPECIAL, INCIDENTAL OR CONSEQUENTIAL DAMAGES.** Your only remedy for any defect in this product is the replacement of the defective product, or a refund of its purchase price, at our option.