

TECHNICAL DATA SHEET

EPS[®] 2426

Styrenated acrylic emulsion for wood edge sealers

MARKET SEGMENTS

Industrial Wood

DESCRIPTION

EPS[®] 2426 is a styrenated acrylic emulsion offering excellent early water resistance when used as a wood edge sealer.

PROPERTIES

- Reduces water swelling when used in board edge sealers for lumber
- Outstanding water resistance
- Low water uptake
- Capable of formulating at low VOC/near 0 VOC
- APE-free *

COMMON APPLICATIONS

Sealer

Specifications

Weight Solids	50.0 +/- 0.7%
Weight/Gallon	8.70 +/- 0.10 lbs.
pH	8.0 - 9.0

Typical Properties

Volume Solids	47.7 +/- 0.7%
T _g	-5°C
Volatile(s)	Water

Suggested Coalescing Solvent(s)

(% Solvent on Binder Solids – Pass 40°F LTC Test)

None Needed

* Made without APE-containing surfactants

Questions? Call EPS Customer Service @ 1-800-654-4242 / Email: info@eps-materials.com

6/26/2020

TECHNICAL SUPPORT: These guidelines are offered to assist the paint formulator in achieving the high performance properties noted and are offered for illustration purposes only; the paint formulator bears sole responsibility for the performance of the final coating product.

SDS: For details on health, safety and handling information, Safety Data Sheets (SDS) are available at www.epscsa.com.

The data on this sheet represent typical values. Since application variables are a major factor in product performance, this information should serve only as a general guide. EPS assumes no obligation or liability for use of this information. UNLESS EPS AGREES OTHERWISE IN WRITING, EPS MAKES NO WARRANTIES, EXPRESS OR IMPLIED, AND DISCLAIMS ALL IMPLIED WARRANTIES INCLUDING WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE OR FREEDOM FROM PATENT INFRINGEMENT. EPS WILL NOT BE LIABLE FOR ANY SPECIAL, INCIDENTAL OR CONSEQUENTIAL DAMAGES. Your only remedy for any defect in this product is the replacement of the defective product, or a refund of its purchase price, at our option. Unless otherwise agreed in writing, all sales of EPS products are governed by the EPS Terms and Conditions of Sale, available at <https://www.epscsa.com/galleries/pdfs/salesterms.pdf>.