

EPS® 2458

Suggested Formulation

EPS® 2458 is a water based, self-crosslinking all-acrylic binder for interior and exterior applications.

PROPERTIES

- Good balance between hardness and flexibility
- Fast dry
- Good chemical resistance
- Very good in-can transparency
- Very good wood wetting (grain accentuation)
- Good block resistance
- Very low solvent demand
- APE-free *

Specifications

Weight Solids	43.0 +/- 1.0%
Viscosity, 23 °C [mPa·s]	100 - 600
pH	7.5 – 8.5

Typical Properties

Volume Solids	40.9 +/- 0.7%
Weight/Gallon	8.70 +/- 0.10 lbs.
MFFT	+5°C
Volatile(s)	Water, ammonia

* Made without APE-containing surfactants

Questions? Call EPS Customer Service @ 1-800-654-4242 / Email: info@eps-materials.com

11/24/2020

TECHNICAL SUPPORT: These guidelines are offered to assist the paint formulator in achieving the high performance properties noted and are offered for illustration purposes only; the paint formulator bears sole responsibility for the performance of the final coating product.

SDS: For details on health, safety and handling information, Safety Data Sheets (SDS) are available at www.epscsa.com.

The data on this sheet represent typical values. Since application variables are a major factor in product performance, this information should serve only as a general guide. EPS assumes no obligation or liability for use of this information. UNLESS EPS AGREES OTHERWISE IN WRITING, EPS MAKES NO WARRANTIES, EXPRESS OR IMPLIED, AND DISCLAIMS ALL IMPLIED WARRANTIES INCLUDING WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE OR FREEDOM FROM PATENT INFRINGEMENT. EPS WILL NOT BE LIABLE FOR ANY SPECIAL, INCIDENTAL OR CONSEQUENTIAL DAMAGES. Your only remedy for any defect in this product is the replacement of the defective product, or a refund of its purchase price, at our option. Unless otherwise agreed in writing, all sales of EPS products are governed by the EPS Terms and Conditions of Sale, available at <https://www.epscsa.com/galleries/pdfs/salesterms.pdf>.

Suggested Formulation

Formula: WD-10 Interior Clear Basecoat

Pounds	Gallons	Raw Material	Supplier	Instructions
768.33	88.31	EPS 2458	EPS	Add in order with good agitation
21.58	2.87	EB (Butyl Cellosolve)	Dow	
8.63	1.09	DB (Butyl Carbitol)	Dow	
52.66	6.32	Water	-	
3.45	0.40	BYK 024	BYK	
3.45	0.42	Siltech C-204	Siltech	
0.86	0.12	Ammonium Hydroxide	-	
0.86	0.09	Mergal K12N	Troy	
3.45	0.38	Acrysol RM-2020NPR	Dow	Adjust to desired viscosity
863.29	100.00	TOTALS		

Formulation Parameters

Weight Solids	39.0 %
Volume Solids	36.8 %
Pigment Volume Conc.	0.0
Calculated VOC Level	93 g/L
Weight/Gallon	8.6 lbs

Typical Properties

pH	7.5-8.5
----	---------

Questions? Call EPS Customer Service @ 1-800-654-4242 / Email: info@eps-materials.com

11/24/2020

TECHNICAL SUPPORT: These guidelines are offered to assist the paint formulator in achieving the high performance properties noted and are offered for illustration purposes only; the paint formulator bears sole responsibility for the performance of the final coating product.

SDS: For details on health, safety and handling information, Safety Data Sheets (SDS) are available at www.epscca.com.

The data on this sheet represent typical values. Since application variables are a major factor in product performance, this information should serve only as a general guide. EPS assumes no obligation or liability for use of this information. UNLESS EPS AGREES OTHERWISE IN WRITING, EPS MAKES NO WARRANTIES, EXPRESS OR IMPLIED, AND DISCLAIMS ALL IMPLIED WARRANTIES INCLUDING WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE OR FREEDOM FROM PATENT INFRINGEMENT. EPS WILL NOT BE LIABLE FOR ANY SPECIAL, INCIDENTAL OR CONSEQUENTIAL DAMAGES. Your only remedy for any defect in this product is the replacement of the defective product, or a refund of its purchase price, at our option. Unless otherwise agreed in writing, all sales of EPS products are governed by the EPS Terms and Conditions of Sale, available at <https://www.epscca.com/galleries/pdfs/salesterms.pdf>.