

# EPS<sup>®</sup> 6607

## LONG OIL ALKYD

# DATA SHEET

### Description

**EPS 6607** is a long oil alkyd. EPS 6607 is designed to provide high gloss, excellent flow and leveling and durability. This balance of properties makes EPS 6607 an excellent choice for architectural enamels and structural steel primers.

- ✓ Excellent flow and leveling
- ✓ Excellent pigment wetting
- ✓ Fast dry
- ✓ Excellent adhesion

### Specifications

*Weight Solids:* 70.0± 0.7%  
*Weight/Gallon:* 8.00 ± 0.10  
*Viscosity:* Z<sub>2</sub> – Z<sub>5</sub>  
*Acid Value:* 5 - 10  
*Color:* 3 - 6

### Suggested Drier Package

#### (% Metal on Resin Solids)

Cobalt	0.07
Calcium	0.07
Zirconium	0.40
Anti-Skin	0.80

### Typical Properties

*Volume Solids:* 63.6 ± 0.7%  
*Solvent* LAMS\*\*/Aromatic 100  
*Composition:* (27.4/2.6)  
*Oil Type:* Soya  
*OH Value:* 50 (theo)  
*Modifier:* None

### Suggested Formulation

None

\*Acid value on solids

\*\*LAMS = Low Aromatic (<1%), Rule 66, Mineral Spirits

111414

**Questions? Call EPS Technical Service @ 1-800-601-8111**

The data on this sheet represent typical values. Since application variables are a major factor in product performance, this information should serve only as a general guide. EPS assumes no obligation or liability for use of this information. **UNLESS EPS AGREES OTHERWISE IN WRITING, EPS MAKES NO WARRANTIES, EXPRESS OR IMPLIED, AND DISCLAIMS ALL IMPLIED WARRANTIES INCLUDING WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR USE OR FREEDOM FROM PATENT INFRINGEMENT. EPS WILL NOT BE LIABLE FOR ANY SPECIAL, INCIDENTAL OR CONSEQUENTIAL DAMAGES.** Your only remedy for any defect in this product is the replacement of the defective product, or a refund of its purchase price, at our option