



HIGH-PERFORMANCE ARCHITECTURAL PRODUCTS

Product	Chemistry	Coating Type	Substrate	Sheen					Properties			Performance Benefits
				Flat	Eggshell	Satin	Semi-Gloss	High Gloss	Solids (%)	pH	MFFT (°C)	
EPS® 2533	Styrenated Acrylic	Primer	Concrete, Exterior Wall, Interior Wall, Masonry/Stucco, Metal, Wood	●					45.5	7.0-8.0	9	<ul style="list-style-type: none"> Interior/Exterior Stain blocking Water resistance
EPS® 2706	All-Acrylic	Topcoat	Concrete, Exterior Wall, Interior Wall, Wood	●	●	●	●		55	8.0-8.5	4	<ul style="list-style-type: none"> Interior/Exterior High alkali stability Abrasion resistance and adhesion
EPS® 2731	All-Acrylic	Topcoat	Concrete, Exterior Wall, Interior Wall, Wood	●	●	●	●		50	8.5-9.0	15	<ul style="list-style-type: none"> Interior/Exterior Dirt pickup resistance Color fade and efflorescence resistance on alkali substrates Surfactant leaching resistance
EPS® 2746	All-Acrylic	Topcoat	Concrete, Exterior Wall, Interior Wall, Wood	●	●	●	●		50	8.5-9.0	10	<ul style="list-style-type: none"> Interior/Exterior Near-zero VOC capable Scrub resistance Stain removal and washability
EPS® 2786	All-Acrylic	Topcoat	Concrete, Exterior Wall, Interior Wall, Masonry/Stucco, Wood				●	●	48	8.5-9.0	21	<ul style="list-style-type: none"> Interior/Exterior Near-zero VOC capable Hardness Dirt pickup and hot block resistance
RayVace® 331	Vinyl Acrylic	Primer	Exterior Wall, Interior Wall, Masonry/Stucco	●					60	4.0-5.0	10	<ul style="list-style-type: none"> Interior Good stability High pigment loading
EPS® 9147	Coalescent	Specialty	-	●	●	●	●	●	>99.1	-	-	<ul style="list-style-type: none"> Low VOC coalescent

All of these polymers are formulated without the use of intentionally added fluorosurfactants.

THE EXPERTISE BEHIND THE INNOVATION

The data on this sheet represents typical values. Since application variables are a major factor in product performance, this information should serve only as a general guide. EPS assumes no obligation or liability for use of this information. UNLESS EPS AGREES OTHERWISE IN WRITING, EPS MAKES NO WARRANTIES, EXPRESS OR IMPLIED, AND DISCLAIMS ALL IMPLIED WARRANTIES INCLUDING WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE OR FREEDOM FROM PATENT INFRINGEMENT. EPS WILL NOT BE LIABLE FOR ANY SPECIAL, INCIDENTAL OR CONSEQUENTIAL DAMAGES. Your only remedy for any defect in this product is the replacement of the defective product, or a refund of its purchase price, at our option. Unless otherwise agreed in writing, all sales of EPS products are governed by the EPS Terms and Conditions of Sale, available at <https://www.epscsa.com/galleries/pdfs/salesterms.pdf>.

CONTACT INFORMATION

EPS Headquarters
1400 N. State St.
Marengo, Illinois 60152

Sales and Customer Service
Phone: 800-654-4242
Email: info@epscsa.com

EPS Technical Service
Phone: 800-654-4242
Email: info@eps-materials.com