

EPS[®] 2550

Styrenated Acrylic Emulsion

MARKET SEGMENT: INDUSTRIAL METAL COMMON APPLICATIONS: PRIMER, TOPCOAT

EPS[®] 2550 is a styrenated acrylic emulsion that can be used to formulate economical coatings offering excellent hardness, gloss, and chemical resistance. Coatings produced with EPS[®] 2550 also exhibit good block resistance and excellent adhesion to plastics, ferrous and non-ferrous metals.

PERFORMANCE BENEFITS

- Hardness
- Gloss development
- Chemical resistance
- Early water resistance
- Multi-substrate adhesion

TYPICAL PROPERTIES

Weight Solids	50.0 ± 0.7%	
Weight/Gallon	8.65 ± 0.10	
рН	7.5 – 8.5	
Volume Solids	48.0 ± 0.7%	
MFFT	> 60° C	
Volatile(s)	Water	

These typical properties do not represent specifications.

SUGGESTED COALESCING SOVENT(S)

(78 Solvent on Binder Solids – Pass 40 F LTC Test)	
EB	35-40%
DB	35-40%

SUGGESTED FORMULATIONS

• EPS 2550 WHT ST1 - High Gloss White Enamel (spray)

Questions? Call EPS Customer Service @ 1-800-654-4242 / Email: info@eps-materials.com SDS: For details on health, safety and handling information, Safety Data Sheets (SDS) are available at www.epscca.com.

The data on this sheet represent typical values. Since application variables are a major factor in product performance, this information should serve only as a general guide. EPS assumes no obligation or liability for use of this information, and the formulator bears sole responsibility for the performance of the final formulated product. UNLESS EPS AGREES OTHERWISE IN WRITING, EPS MAKES NO WARRANTIES, EXPRESS OR IMPLIED, AND DISCLAIMS ALL IMPLIED WARRANTIES INCLUDING WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE OR FREEDOM FROM PATENT INFRINGEMENT. EPS WILL NOT BE LIABLE FOR ANY SPECIAL, INCIDENTAL OR CONSEQUENTIAL DAMAGES. Your only remedy for any defect in this product is the replacement of the defective product, or a refund of its purchase price, at our option. Unless otherwise agreed in writing, all sales of EPS products are governed by the EPS Terms and Conditions of Sale, available at https://www.epscca.com/galleries/pdfs/salesterms.pdf.