

## TECHNICAL DATA SHEET

# **EPS® 541**

**Acrylic copolymer** 

### **MARKET SEGMENTS**

**Industrial Maintenance** 

#### DESCRIPTION

EPS® 541 is a versatile and robust acrylic copolymer in water, offering excellent corrosion resistance, early water resistance, and adhesion to multiple substrates.

#### **PROPERTIES**

- Excellent gloss potential
- Excellent gloss retention
- Excellent block resistance
- Excellent exterior durability
- Excellent resistance to dirt pickup
- Excellent chemical and corrosion resistance

#### **COMMON APPLICATIONS**

Primer, topcoat

Specifications	
Weight Solids	50.0 ± 1%
Viscosity, 23 °C [mPa·s]	< 500
Hq	7.5 - 8.5

Typical Properties	
MFFT	+57° C
Density @ 20 °C [kg/m3]	1044

EPS<sup>®</sup> 541 should be stored in a closed container at a dry place at storage temperatures between 5 °C and 30 °C. Under the above-mentioned storage condition, the stability will be 6 months.

Questions? Call EPS Customer Service @ +31 78 683 3250 / Email: info.nl@eps-materials.com

1/5/2022

**TECHNICAL SUPPORT:** These guidelines are offered to assist the paint formulator in achieving the high performance properties noted and are offered for illustration purposes only; the paint formulator bears sole responsibility for the performance of the final coating product.

SDS: For details on health, safety and handling information, Safety Data Sheets (SDS) are available at www.epscca.com.

The data on this sheet represent typical values. Since application variables are a major factor in product performance, this information should serve only as a general guide. EPS assumes no obligation or liability for use of this information. UNLESS EPS AGREES OTHERWISE IN WRITING, EPS MAKES NO WARRANTIES, EXPRESS OR IMPLIED, AND DISCLAIMS ALL IMPLIED WARRANTIES INCLUDING WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE OR FREEDOM FROM PATENT INFRINGEMENT. EPS WILL NOT BE LIABLE FOR ANY SPECIAL, INCIDENTAL OR CONSEQUENTIAL DAMAGES. Your only remedy for any defect in this product is the replacement of the defective product, or a refund of its purchase price, at our option. Unless otherwise agreed in writing, all sales of EPS products are governed by the EPS Terms and Conditions of Sale, available at https://www.epscca.com/galleries/pdfs/salesterms.pdf.