

EPS BV P.O. Box 358, 3340 AJ H.I.Ambacht Nijverheidsweg 35, 3341 LJ H.I.Ambacht The Netherlands T : +31 78 6833250 F : +31 78 6812697 info.nl@eps-materials.com

# DYFLEX<sup>®</sup> LP 2721

# **DATA SHEET**

# **Description**

DYFLEX<sup>®</sup> LP 2721 is a PU-acrylate hybrid for high quality parket, furniture and plastic.

## **Properties**

DYFLEX<sup>®</sup> LP 2721 exhibits very good mechanical and chemical resistance combined with abrasion resistance.

## Physical data

Solids by weight [%]:	38.0 ± 1
Viscosity, 23 °C [mPa·s]:	< 250
(Brookfield, Spindle 2)	
pH value [-]:	7.5 – 8.5

#### Typical values

MFFT [°C]:	+ 12
Density @ 20 °C [kg/m <sup>3</sup> ]:	1055
Neutralized with:	TEA (bonded as a salt)

#### Storage

DYFLEX<sup>®</sup> LP 2721 should be stored in a closed container at a dry place at storage temperatures between 5 °C and 30 °C.

#### <u>Stability</u>

Under the above mentioned storage condition the stability will be 6 months ex works.

The data on this sheet represent typical values. Since application variables are a major factor in product performance, this information should serve only as a general guide. EPS assumes no obligation or liability for use of this information. UNLESS EPS AGREES OTHERWISE IN WRITING, EPS MAKES NO WARRANTIES, EXPRESS OR IMPLIED, AND DISCLAIMS ALL IMPLIED WARRANTIES INCLUDING WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR USE OR FREEDOM FROM PATENT INFRINGEMENT. EPS WILL NOT BE LIABLE FOR ANY SPECIAL, INCIDENTAL OR CONSEQUENTIAL DAMAGES. Your only remedy for any defect in this product is the replacement of the defective product, or a refund of its purchase price, at our option. Date of issue: February 2016