



# NovoColor® HP

## Low VOC Water-Only Colorant

### Technical Data Sheet

PRODUCT NUMBER	MASS TONE	TINT	PRODUCT CODE	PRODUCT NAME	CI PIGMENT NAME	TYPICAL PROPERTIES						
						DENSITY		% PRIME PIGMENT BY WT.	% INERT PIGMENT BY WT.	% TOTAL SOLIDS BY WT.	Theoretical VOC (g/L)	% WATER BY WEIGHT
						lbs/gal	g/cc					
8900N			KX	White	PW 6	16.8	2.0	56.1	9.2	73.4	0.00	26.6
8913N			AXXN	High Strength Organic Yellow	PY 74	9.4	1.1	32.6	0.4	49.4	0.01	50.6
8915N			TT	High Strength Medium Yellow	Blend	9.8	1.2	38.2	3.1	55.6	0.01	44.4
8916N			ANN	Durable Yellow	Blend	15.1	1.8	52.2	3.8	66.0	0.02	34.0
8920N			DD	Phthalo Green	PG 7	11.6	1.4	20.6	25.0	59.3	0.01	40.7
8921N			D	Phthalo Green	PG 7	12.4	1.5	8.7	42.7	61.8	0.03	38.2
8930N			EE	Phthalo Blue	PB 15:2	10.9	1.3	14.5	27.5	55.5	0.01	44.5
8932N			E	Phthalo Blue	PB 15:2	12.1	1.4	6.4	43.3	60.7	0.03	39.3
8935N			F	Red Iron Oxide	PR 101	18.1	2.2	63.0	3.8	76.5	0.01	23.5
8938N		n/a	TRO	Transoxide Red	PR 101	11.8	1.4	34.8	0.6	57.7	0.23	42.3
8942N			IR	Interior Red	PR 112	11.7	1.4	11.0	32.7	51.8	0.01	48.2
8951N			RR	High Strength Exterior Red	PR 254	12.3	1.5	14.9	32.9	59.1	0.00	40.9
8964N			OO	High Strength Orange	PO 73	10.7	1.3	25.3	21.4	59.9	0.00	40.1
8970N		n/a	TYO	Transoxide Yellow	PY 42	11.2	1.3	27.0	2.8	49.2	0.01	50.8
8978N			C	Yellow Oxide	PY 42	15.4	1.8	56.8	1.7	70.7	0.01	29.3
8983N			MM	High Strength Magenta	PR 122	10.4	1.2	14.7	22.8	50.3	0.03	49.7
8988N			L	Raw Umber	PBr 7	11.6	1.4	19.7	18.8	54.4	0.02	45.6
8991N			B	Lamp Black	PBk 7	11.8	1.4	9.2	31.8	50.1	0.01	49.9
8997N			I	Brown Oxide	Blend	13.2	1.6	26.3	21.6	56.5	0.01	43.5

The data on this sheet represent typical values. Since application variables are a major factor in product performance, this information should serve only as a general guide. CCA assumes no obligation or liability for use of this information. **UNLESS CCA AGREES OTHERWISE IN WRITING, CCA MAKES NO WARRANTIES, EXPRESS OR IMPLIED, AND DISCLAIMS ALL IMPLIED WARRANTIES INCLUDING WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR USE OR FREEDOM FROM PATENT INFRINGEMENT. CCA WILL NOT BE LIABLE FOR ANY SPECIAL, INCIDENTAL OR CONSEQUENTIAL DAMAGES.** Your only remedy for any defect in this product is the replacement of the defective product, or a refund of its purchase price, at our option.