



NovoColor® IP

Low VOC Waterborne Colorant Line

Technical Data Sheet

PRODUCT NUMBER	MASS-TONE	TINT	PRODUCT NAME	AVAILABILITY	CI PIGMENT NAME	Typical Properties					
						DENSITY		% PRIME PIGMENT BY WT.	% TOTAL SOLIDS BY WT.	% WATER BY WT.	VOC g/L (EPA Method 24)
						lbs/gal	g/cc				
8500			White	Stock	PW 6	16.8	2.02	66.6	76.7	23.3	0.0
8511			Organic Yellow	Stock	PY 97	10.0	1.19	40.5	54.9	45.1	0.0
8513			Organic Yellow G/S	Stock	PY 74	9.7	1.17	47.3	61.6	38.4	0.0
8514			Organic Yellow R/S	Stock	PY 65	9.5	1.14	40.4	54.4	45.6	0.0
8515			Organic Med. Yellow	Stock	PY 83	10.0	1.19	49.7	60.1	39.9	0.0
8518			Exterior Yellow	Stock	PY 184	17.1	2.05	61.0	70.2	29.8	0.0
8522			Phthalo Green	Stock	PG 7	11.2	1.34	43.7	60.5	39.5	0.0
8531			Phthalo Blue	Stock	PB 15	9.4	1.13	28.1	51.2	48.8	0.0
8532			Phthalo Blue	Stock	PB 15	9.4	1.13	33.8	52.3	47.7	0.0
8533			Ultra Marine Blue	Stock	PB 29	12.2	1.46	53.8	61.2	38.8	0.0
8538T		n/a	Trans Oxide Red	Stock	PR 101	11.7	1.41	35.1	56.3	43.7	5.4
8539			Carbazole Violet	MTO	PV 23	9.9	1.18	14.7	50.3	49.7	0.0
8542			Organic Red	Stock	PR 170	9.3	1.11	33.9	51.8	48.2	0.0
8543			Naphthol Red	Stock	PR 112	9.6	1.15	34.4	57.9	42.1	0.0
8544C			Quinacridone Red	Stock	PR 209	9.4	1.12	24.4	43.1	56.9	0.0
8545			Red Oxide	Stock	PR 101	18.5	2.22	67.6	79.6	20.4	0.0
8546			High Hiding Durable Red	Stock	Blend	9.5	1.14	33.6	53.5	46.5	0.0
8549			Quinacridone Magenta	Stock	Blend	9.6	1.15	26.5	44.8	55.2	0.0



NovoColor® IP

Low VOC Waterborne Colorant Line

Technical Data Sheet

PRODUCT NUMBER	MASS-TONE	TINT	PRODUCT NAME	AVAILABILITY	CI PIGMENT NAME	Typical Properties					
						DENSITY		% PRIME PIGMENT BY WT.	% TOTAL SOLIDS BY WT.	% WATER BY WT.	VOC g/L (EPA Method 24)
						lbs/gal	g/cc				
8566			DPP Orange	Stock	PO 73	8.7	1.04	15.1	25.1	74.9	0.0
8567			Pyrazolone Orange	Stock	PO 13	9.4	1.13	32.9	63.3	36.7	0.0
8569			Azo Orange	Stock	PO 74	11.4	1.37	14.5	60.9	39.1	0.0
8570T		n/a	Trans Oxide Yellow	Stock	PY 42	11.0	1.32	30.0	49.4	50.6	5.2
8573			Orange Oxide	Stock	PY 42	14.0	1.68	53.5	68.2	31.8	0.0
8576			Yellow Oxide	Stock	PY 42	15.8	1.89	60.5	74.8	25.2	0.0
8580			Quinacridone Violet	Stock	PV 19	8.9	1.07	13.2	27.0	73.0	0.0
8582			Quinacridone Magenta	Stock	PR 122	9.6	1.15	36.7	48.7	51.3	0.0
8588			Raw Umber	Stock	PBR 7	11.6	1.39	17.6	66.4	33.6	0.0
8589			Black Iron Oxide	MTO	PBK 26	16.8	2.02	61.6	76.8	23.2	0.0
8590			Weak Black	Stock	PBK 7	11.0	1.32	3.0	51.2	48.8	0.0
8591			Lamp Black	Stock	PBK 7	10.0	1.20	10.8	53.5	46.5	0.2
8592			High Strength Lamp Black	Stock	PBK 7	10.6	1.27	28.8	61.1	38.9	0.0
8594			Carbon Black	Stock	PBK 7	10.2	1.22	39.5	51.3	48.7	0.0
8596			Carbon Black	Stock	PBK 7	9.8	1.18	33.3	41.1	58.9	0.0
8597			Brown Oxide	Stock	Blend	13.1	1.56	29.1	66.7	33.3	0.6

The data on this sheet represent typical values. Since application variables are a major factor in product performance, this information should serve only as a general guide. CCA assumes no obligation or liability for use of this information. **UNLESS CCA AGREES OTHERWISE IN WRITING, CCA MAKES NO WARRANTIES, EXPRESS OR IMPLIED, AND DISCLAIMS ALL IMPLIED WARRANTIES INCLUDING WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR USE OR FREEDOM FROM PATENT INFRINGEMENT. CCA WILL NOT BE LIABLE FOR ANY SPECIAL, INCIDENTAL OR CONSEQUENTIAL DAMAGES.** Your only remedy for any defect in this product is the replacement of the defective product, or a refund of its purchase price, at our option.

ver 12.2017