



NovoColor® SF

Transparent Pigment Dispersions

Technical Data Sheet

PRODUCT NUMBER	MASS TONE	COLORANT NAME	CI PIGMENT NAME	Typical Properties				
				DENSITY LB/GAL	DENSITY g/cc	% PRIME PIGMENT BY WT.	% TOTAL SOLIDS BY WT.	% WATER BY WEIGHT
8114	Yellow	Medium Yellow	PY83	9.4	1.1	34.0%	62.8%	37.2%
8115	Orange	Golden Yellow	PY110	9.3	1.1	20.0%	44.5%	55.5%
8122	Green	Phthalo Green	PG7	9.9	1.2	31.8%	58.6%	41.4%
8132	Blue	Phthalo Blue	PB15:3	9.6	1.2	32.5%	71.2%	28.8%
8138	Red	Trans Oxide Red	PR101	12.9	1.5	37.6%	64.9%	35.1%
8140	Purple	Carbazole Violet	PV23	9.3	1.1	18.2%	55.5%	44.5%
8142	Red	Organic Red	PR166	9.1	1.1	20.0%	44.3%	55.7%
8144	Red	Rubine Red	PR184	9.7	1.2	37.2%	64.0%	36.0%
8146	Red	DPP Red	PR254	9.2	1.1	24.6%	46.1%	53.9%
8149	Magenta	Magenta	PR122	9.5	1.1	29.7%	54.8%	45.2%
8170	Yellow	Trans Oxide Yellow	PY42	12.9	1.5	33.1%	70.3%	29.7%
8194	Black	Carbon Black	PBK7	9.8	1.2	32.1%	73.4%	26.6%

The data on this sheet represent typical values. Since application variables are a major factor in product performance, this information should serve only as a general guide. CCA assumes no obligation or liability for use of this information. UNLESS CCA AGREES OTHERWISE IN WRITING, **CCA MAKES NO WARRANTIES, EXPRESS OR IMPLIED, AND DISCLAIMS ALL IMPLIED WARRANTIES INCLUDING WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR USE OR FREEDOM FROM PATENT INFRINGEMENT. CCA WILL NOT BE LIABLE FOR ANY SPECIAL, INCIDENTAL OR CONSEQUENTIAL DAMAGES.** Your only remedy for any defect in this product is the replacement of the defective product, or a refund of its purchase price, at our option.